

TerraTex® OL-I

TerraTex® nonwoven geotextiles are made up of polypropylene fibers. These fibers are needled to form a stable and durable network such that the fibers retain their relative position. It is non-biodegradable and resistant to most soil chemicals, acids, and alkali with a pH range of 3 to 12. Unless noted otherwise, all values are minimum average roll values (MARV).

| Property | Test Method | English | Metric |
|-------------------------------|-------------|----------------|----------------------|
| Weight (Typical) ¹ | ASTM D5261 | 4.1 oz/sy | 139 g/m ² |
| Grab Tensile | ASTM D4632 | 102 lbs | 0.453 kN |
| Grab Elongation | ASTM D4632 | 50 % | 50 % |
| Trapezoid Tear | ASTM D4533 | 45 lbs | 0.20 kN |
| CBR Puncture | ASTM D6241 | 300 lbs | 1.33 kN |
| Asphalt Retention | | 0.24 sy | 1.1 L/m ² |
| Melting Point | | 300 °F | 150 °C |
| UV Resistance | ASTM D4355 | 70 % @ 500 hrs | 70 % @ 500 hrs |

1. At the time of manufacturing. Handling, storage, and shipping may change these properties.

2. Value represents maximum avg roll value

3. Specifications can vary by project. Please contact local sales rep for technical assistance and product selection.

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.